

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 04-178439

(43)Date of publication of application : 25.06.1992

(51)Int.Cl.

C08J 9/04
C08K 7/22
C08L 63/00
// B64C 1/00
C08L 63:00

(21)Application number : 02-306595

(71)Applicant : NIPPON PETROCHEM CO LTD

(22)Date of filing : 13.11.1990

(72)Inventor : IWAI SAKUYA
SASAKI KOICHIRO
OSHIMA AKIO

(54) EPOXY RESIN COMPOSITION FOR LIGHT-WEIGHT COMPOSITE MATERIAL, INTERMEDIATE AND COMPOSITE MATERIAL

(57)Abstract

PURPOSE: To obtain a high-strength and lightweight composition for lightweight composite materials suitable for inner core materials, etc., being readily laminated, co-crosslinkable with other prepreg by blending an epoxy resin with specific amounts of fine hollow spheres, a blowing agent and a curing agent.

CONSTITUTION: (A) 50-95 pts.wt. epoxy resin is blended with (B) 5-35 pts.wt. fine hollow spheres (e.g. glass or alumina silicate), (C) 0.1-15 pts.wt. blowing agent (e.g. azobisisobutyronitrile), (D) 0.5-10 pts.wt. curing agent (e.g. dicyan) and (E) 0.5-10 pts.wt. curing promoter (e.g. 3-phenyl-1,1-dimethylurea). The composition is molded into a sheetlike or filmy state to give a single material intermediate for composite material, which is used to give lightweight composite materials or foamed and cured to give lightweight composite materials. Or a reinforced intermediate is obtained from the intermediate and the reinforcing material and processed to give lightweight composite materials or foamed and cured to give lightweight composite materials.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]